PATENT ABSTRACTS OF JAPAN

(11)Publication number:

11-092751

(43) Date of publication of application: 06.04.1999

(51)Int.Cl.

CO9K 3/16 C08K 5/42 5/55

(21)Application number : 10-206790

(71)Applicant: SANYO CHEM IND LTD

(22) Date of filing:

22.07.1998

(72)Inventor: MUKAI TAKAO

SATAKE SOICHI **ICHIHARA EIJI**

(30)Priority

Priority number: 09215530


Priority date : 25.07.1997

Priority country: JP

(54) ANTISTATIC AGENT HAVING EXCELLENT HEAT RESISTANCE USED FOR RESIN, AND ANTISTATIC RESIN COMPOSITION

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain an antistatic agent not undergoing heat decomposition during thermal molding or heating by using a compound having a counter anion being a super strong acid and one cationic group bonded to a nonionic molecular chain. SOLUTION: This compound is represented by the formula (wherein Q is N or P; R1 to R4 are each contains a nonionic molecular chain in the group (provided that two of them may be combined with each other to form a ring); and X is an anion of a super acid). The counter anion is desirably a super strong acid having a Hammett's acidity function (-H0) of 12 or above and is exemplified by a super strong acid (tetrafluoroboric acid or hexafluorophosphoric acid)



Searching PAJ Page 2 of 2

derived from a combination of a proton acid with a Lewis acid or trifluoromethanesulfonic acid. The amount of the antistatic agent added to a resin is usually 0.1/99.9 to 10/90 in terms of an antistatic agent/thermoplastic resin weight ratio.

LEGAL STATUS

[Date of request for examination]

24.08.1998

[Date of sending the examiner's decision of

rejection]

[Kind of final disposal of application other than

the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

2909735

[Date of registration]

09.04.1999

[Number of appeal against examiner's

decision of rejection]

[Date of requesting appeal against examiner's

decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office